



West Yorkshire Materials Testing Service

Page 1 of 1

PO Box 5, Morley, LS27 0QP
Nepshaw Lane South, Morley, Leeds
Tel 0113 253 0241 Fax 0113 252 7029
Head of Laboratory G. Briggs C. Text ATI

Client: Camira Fabrics
Hopton Mills
Mirfield
WF14 8HE

Entry No: 36368 (Amended)

Date Received: 17th July 2008

Client's Description: Sample of Fabric "The Savile Row Collection"

TEST REPORT

Test Required:	Abrasion in accordance with BS EN 11465 and BS 2513 : 2004
Date of Test:	25.7.06 to 4.8.06
Conditioning:	24 hours at 65 +/- 4% Relative Humidity, 20 +/- 2°C
Method of Test:	BS EN ISO 12947-2 : 1999

The tests were carried out using a pressure of 12 ± 0.3 kPa. The criterion for judging end point was three threads broken.

Specimen 1	100,000 rubs
Specimen 2	150,000 rubs (No end point)
Specimen 3	110,000 rubs
Specimen 4	130,000 rubs
Overall Result	100,000 rubs

Change in colour after 3,000 pulses: - 5

Observation Technique:- 10 fold magnification
Type of Fabric:- Flat Woven

Comments

Comments
On the basis of the tests carried out this sample of fabric has a Performance Level Category Rating A (over 45,000 rubs) as specified in Table 1 of BS EN 14465: 2003.

When compared with BS 2543 : 2004 this sample of fabric satisfies the requirements of fabrics for severe contract use.

-- End of Document

This is hereby certified to be a correct return of the tests made of the items referred to herein. G. Price, Head of Laboratory

200

G Briggs, Head of Laboratory
Date of original 6th August 2008
Date of amendment 7th January 2009

Unless instructed otherwise by the client sample remnants will be disposed of after 28 days.



- * Test marked (*) in this certificate are not included in the UKAS Accreditation Schedule for this Laboratory.
- * Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.
- * This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.

