

West Yorkshire Materials Testing Service

PO Box 5, Morley, LS27 0QP
Nepshaw Lane South, Morley, Leeds
Tel 0113 253 0241 Fax 0113 252 7029
Head of Laboratory G. Briggs C. Text ATI

Client: Camira Fabrics Ltd
Hopton Mills
Mirfield
West Yorkshire
WF148HE

Entry No: 35355

Date received: 07/03/2008

Client's Description: Sample of fabric "Urban"

TEST REPORT

Test Required: Flammability BS 7176 Medium Hazard
Pre-treatment: none
Conditioning: A minimum of 24 hours at 50 +/- 5% Relative Humidity, 23 +/- 2° C
Method of Test: BS EN 1021-1:2006 – smouldering cigarette
BS EN 1021-2:2006 – match flame equivalent
Date of Test: 11/03/2008

| Ignition Source | Observations | Result |
|------------------------|--|--------|
| Smouldering cigarette | No flaming or progressive smouldering was observed within one hour of placement of the cigarettes. | PASS |
| Match flame equivalent | Flaming ceased within the specified two minute period after removal of the butane flame and no progressive smouldering occurred. | PASS |

Note: A 35 kg/m³ CMHR Foam (Kay Metzler 35H) which meets the requirements of Annex A of BS 7176 was used as the filling

The above tests relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

-----End of Page-----

This is hereby certified to be a correct return of the tests made of the items referred to herein.

G Briggs
Head of Laboratory
31st March 2008


Unless instructed otherwise by the client sample remnants will be disposed of after 28 days.

- * Test marked (*) in this certificate are not included in the UKAS Accreditation Schedule for this Laboratory.
- * Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.
- * This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.



1104





West Yorkshire Materials Testing Service

PO Box 5, Morley, LS27 0QP
Nepshaw Lane South, Morley, Leeds
Tel 0113 253 0241 Fax 0113 252 7029
Head of Laboratory G. Briggs C. Text ATI

Client: Camira Fabrics Ltd
Hopton Mills
Mirfield
West Yorkshire
WF148HE

Entry No: 35355

Method of Test: BS 5852 : 2006 Clause 11 (composites)

Pre-treatment: none

Conditioning: A minimum of 96 hours at 50 +/- 20% Relative Humidity, 20 +/- 5° C

Date of Test: 11/03/2008

The following test results relate only to the ignitability of the combination of upholstery composites under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

| Ignition Source | Observations | Result |
|-----------------|---|--------|
| 5 (Wood Crib) | Flaming ceased within the specified ten minute period after ignition of the crib and no progressive smouldering occurred. | PASS |

Note: A 35 kg/m³ CMHR Foam (Kay Metzler 35H) which meets the requirements of Annex A of BS 7176 was used as the filling

Comments

BS 7176 : 2007 relates to labelling of furniture. If an item of furniture was manufactured from a composite of the fabric and foam tested above then it would comply with the medium hazard category requirements.

-----End of Document-----

This is hereby certified to be a correct return of the tests made of the items referred to herein.

G Briggs
G Briggs
Head of Laboratory
31st March 2008

Unless instructed otherwise by the client sample remnants will be disposed of after 28 days.



1104

* Test marked (*) in this certificate are not included in the UKAS Accreditation Schedule for this Laboratory.

* Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.

* This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.



TRA09786