

Client: Camira Fabrics Ltd
Meltham Mills
Meltham
West Yorkshire
HD9 4AY

Entry No: 66056-01

Date received: 11/07/2014

Client's Description: Sample of Fabric Mainline Flax Hillingdon (221051) Call 2520

TEST REPORT

Test Required: Abrasion in accordance with BS EN 14465

Conditioning: In accordance with BS EN ISO 139:2005 for a minimum of 24 hours at 65+/-4% Relative Humidity , 20+/-2°C.

Method of Test: BS EN ISO 12947-2:1999

Date of Test: 17.7.14 to 23.7.14

The tests were carried out using a pressure of 12+/-0.3kPa.
The criterion for judging end point was three threads broken.

Specimen 1	50,000 Rubs
Specimen 2	50,000 Rubs
Specimen 3	55,000 Rubs
Specimen 4	50,000 Rubs
Overall Result	50,000 Rubs

Change in colour after 3,000 rubs 4-5

Observation Technique:- 10 Fold Magnification
Type of Fabric:- Flat Woven

Comments

When compared with BS 2543:2004 this sample of fabric satisfies the requirements of fabrics for severe contract use.

-----End of Document-----

This is hereby certified to be a correct return of the tests made of the items referred to herein.



Geoff Briggs C.Text., A.T.I.
Head of laboratory
30th July 2014



- ❖ Unless instructed otherwise by the client sample remnants will be disposed of after 28 days
- ❖ Test marked (*) in this certificate are not included in the UKAS Accreditation Schedule for this Laboratory.
- ❖ Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.
- ❖ This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.

