



# NZWTA



All tests reported  
herein have been  
performed in accordance  
with the laboratory's  
scope of accreditation

## No. 1367334.8

(Please quote this number in all correspondence)

CLIENT:  
Textilia Ltd.  
PO Box 37 378  
Parnell, Auckland  
  
Attn.: Therese Ronalde

SAMPLE RECEIVED FROM:  
Textilia Ltd.

Date Received: 25.3.21

SAMPLE DESCRIPTION:  
Drapery fabric – Lund  
Nominal Composition – 100% Polyester  
Nominal Weight – 785g per lineal meter

Client Order No.:

Client Reference:

1 of 2

### AS 1530.2-1993 – METHODS FOR FIRE TESTS ON BUILDING MATERIALS, COMPONENTS AND STRUCTURES PART 2: TEST FOR FLAMMABILITY OF MATERIALS

- Samples conditioned at 65% RH and 20°C
- Date tested: 6/4/2021
- Samples tested as received.
- Tested face and back alternately.
- The specimen is mounted vertically on a frame and a flame is applied to its base. The maximum height reached by the flame in a predetermined time or the time taken for the tip of the flame to reach a predetermined height is recorded together with the air temperature in a flue mounted above the specimen. From these results the flammability index is calculated using the highest result.

|                           | Length                            | Width |
|---------------------------|-----------------------------------|-------|
| Maximum Height (D) – Mean | 4.8                               | 3.8   |
| CV%                       | 43.8                              | 44.9  |
| Time (t) – Mean           | N/A                               | N/A   |
| CV%                       | N/A                               | N/A   |
| Heat (A) – Mean (°C.min.) | 5.9                               | 3.1   |
| CV%                       | 39.4                              | 52.8  |
| Number of Test Specimens  | 9                                 | 9     |
| Observation               | Visible smoke, melting, dripping. |       |

|                   | Length | Width |
|-------------------|--------|-------|
| Speed Factor (S)  | N/A    | N/A   |
| Spread Factor (E) | 4      | 2     |
| Heat Factor (H)   | 1      | 1     |

Flammability Index calculation:  $I = H + E$  or  $I = H + S$

**Flammability Index = 5**

These test results relate only to the behaviour of the test specimens of the material under the particular conditions of the test, and they are not intended to be the sole criterion for assessing the potential fire hazard of the material in use.

**Note:** When arithmetic calculations for S, E or H give a negative result, this is reported as zero.

#### "THIS REPORT APPLIES ONLY TO THE SAMPLES TESTED"

Samples and their identifying descriptions have been provided by the client unless otherwise stated. NZWTA Ltd makes no warranty, implied or otherwise as to the source of the tested samples. The above results are designed to provide THE CLIENT WITH GUIDANCE INFORMATION ONLY. This document shall not be reproduced except in full.

L A Greer  
Signatory

  
C Judan  
Signatory

07/04/2021

New Zealand Wool Testing Authority Ltd

22 Bridge Street, PO Box 12065

Ahuriri, Napier 4144, New Zealand

T +64 6 835 1086, F +64 6 835 6473 Email: testing@nzwta.co.nz



# NZWTA



All tests reported  
herein have been  
performed in accordance  
with the laboratory's  
scope of accreditation

## No. 1367334.8

(Please quote this number in all correspondence)

CLIENT:  
Textilia Ltd.  
PO Box 37 378  
Parnell, Auckland

Attn.: Therese Ronalde

SAMPLE RECEIVED FROM:  
Textilia Ltd.

Date Received: 25.3.21

SAMPLE DESCRIPTION:  
Drapery fabric – Lund  
Nominal Composition – 100% Polyester  
Nominal Weight – 785g per lineal meter

Client Order No.:

Client Reference:

2 of 2



**"THIS REPORT APPLIES ONLY TO THE SAMPLES TESTED"**

Samples and their identifying descriptions have been provided by the client unless otherwise stated. NZWTA Ltd makes no warranty, implied or otherwise as to the source of the tested samples. The above results are designed to provide THE CLIENT WITH GUIDANCE INFORMATION ONLY. This document shall not be reproduced except in full.

L A Greer  
Signatory

  
C Judan  
Signatory

07/04/2021

**New Zealand Wool Testing Authority Ltd**

22 Bridge Street, PO Box 12065

Ahuriri, Napier 4144, New Zealand

T +64 6 835 1086, F +64 6 835 6475 Email: testing@nzwtal.co.nz