

**No. 1176344.8**

(Please quote this number in all correspondence)

CLIENT:  
Textilia Ltd.  
PO Box 37-378  
Parnell,  
Auckland 1052

SAMPLE RECEIVED FROM:

Date: 29.3.17

Attn. Alicia Dann

SAMPLE DESCRIPTION:

Woven fabric Flusso for drapery , 100% Polyester,  
132 gsm, Canyon colour.

Client Order No.:

Client Reference:

1 of 1

**AS 1530.2-1993 – METHODS FOR FIRE TESTS ON BUILDING MATERIALS, COMPONENTS AND STRUCTURES PART 2: TEST FOR FLAMMABILITY OF MATERIALS**

This test was carried out by a NATA accredited subcontracted laboratory

Samples tested as received.

When face and back are tested, the worst results are quoted.

	Length	Width
Maximum Height ( <i>D</i> ) – Mean	3.9	4.0
CV%	5.2	0.0
Time ( <i>t</i> ) – Mean	N/A	N/A
CV%	N/A	N/A
Heat ( <i>A</i> ) – Mean (°C.min.)	1.5	1.5
CV%	0.0	0.0
Number of Test Specimens	6	6
Observation	Melting	

	Length	Width
Speed Factor ( <i>S</i> )	N/A	N/A
Spread Factor ( <i>E</i> )	2	2
Heat Factor ( <i>H</i> )	1	1

Flammability Index calculation:  $I = H + E$  or  $I = H + S$ **Flammability Index = 3**

These test results relate only to the behaviour of the test specimens of the material under the particular conditions of the test, and they are not intended to be the sole criterion for assessing the potential fire hazard of the material in use.

Observation : visible smoke and melting

**"THIS REPORT APPLIES ONLY TO THE SAMPLES TESTED"**

Samples and their identifying descriptions have been provided by the client unless otherwise stated. NZWTA Ltd makes no warranty, implied or otherwise as to the source of the tested samples. The above results are designed to provide THE CLIENT WITH GUIDANCE INFORMATION ONLY. This document shall not be reproduced except in full.

*LA*  
L A Greer  
Signatory

C Judan  
Signatory

06/04/2017

**New Zealand Wool Testing Authority Ltd**

Cnr Bridge &amp; Lever Streets, PO Box 12065

Ahuriri, Napier 4144, New Zealand

T +64 6 835 1086, F +64 6 835 6473 Email: testing@nzwta.co.nz