

Our Ref: SW/BR

27 April 2020

Report 361739

Page 1 of 3

Camira Fabrics Limited
Meltham Mills
Meltham
Huddersfield
West Yorkshire
HD9 4AY

Contact: Anthony Croall

DATE RECEIVED : 23 APR 2020
 QUALITY/REFERENCE : RIVET
 REPUTED FIBRE CONTENT : NOT GIVEN
 FABRIC DESCRIPTION : WOVEN
 COLOUR/DESIGN : LAGOON HEGL35, GALVANISE HEGL26, VITREOUS HEGL01
 ORDER NUMBER : S516680

PERFORMANCE STANDARD : GENERAL



REPORT SUMMARY

Tests	Method	Pass	Fail	Requirement
Chlorinated water	BS EN ISO 105-E03:2010 Chlorinated Water			No requirement
Chlorinated water	BS EN ISO 105-E03:2010 Chlorinated Water			No requirement
Chlorinated water	BS EN ISO 105-E03:2010 Chlorinated Water			No requirement



118 Lupton Avenue Leeds LS9 6ED
 Tel:0044 (0) 113 248 8830 Fax:0044 (0) 113 248 0239 EMail: info@hstts.co.uk
 Registered No. 2899980 VAT No. 613 4310 86

27 April 2020

Report 361739

Page 2 of 3



S. WISEMAN
LABORATORY DIRECTOR

This report may not be reproduced except in full without the written approval of HSTTS. In all circumstances results of tests are implied as referring only to the sample supplied and should not be construed or interpreted on any other basis. The comments given in the report are for guidance only and are not a part of the results. Where specified in a test method, preconditioning in accordance with ISO 139 is not carried out as samples are exposed to the conditioning atmosphere specified within ISO 139 for a minimum of 16 hours prior to test.



118 Lupton Avenue Leeds LS9 6ED
Tel:0044 (0) 113 248 8830 Fax:0044 (0) 113 248 0239 EMail: info@hstts.co.uk
Registered No. 2899980 VAT No. 613 4310 86

Report 361739

COLOUR FASTNESS TO:

BS EN ISO 105-E03:2010 Chlorinated Water

Lagoon 10% Chlorine Solution

	Shade change	Requirement:
	4-5	No requirement

BS EN ISO 105-E03:2010 Chlorinated Water

Galvanise 10% Chlorine Solution

	Shade change	Requirement:
	4-5	No requirement

BS EN ISO 105-E03:2010 Chlorinated Water

Vitreous 10% Chlorine Solution

	Shade change	Requirement:
	4-5	No requirement
